

Revised PCT/PTO 19 OCT 2004


PCT/EP03/04259



Europäisches
Patentamt

European
Patent Office

Office européen
des brevets



PCT/EP03/4259

Bescheinigung

Certificate

Attestation

Die angehefteten Unterla-
gen stimmen mit der
ursprünglich eingereichten
Fassung der auf dem näch-
sten Blatt bezeichneten
europäischen Patentanmel-
dung überein.

The attached documents
are exact copies of the
European patent application
described on the following
page, as originally filed.

Les documents fixés à
cette attestation sont
conformes à la version
initialement déposée de
la demande de brevet
européen spécifiée à la
page suivante.

Patentanmeldung Nr. Patent application No. Demande de brevet n°

02405349.8

**PRIORITY
DOCUMENT**
SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)

Der Präsident des Europäischen Patentamts;
Im Auftrag

For the President of the European Patent Office

Le Président de l'Office européen des brevets
p.o.

R C van Dijk



Europäisches
Patentamt

European
Patent Office

Office européen
des brevets

Anmeldung Nr:
Application no.: 02405349.8
Demande no:

Anmeldetag:
Date of filing: 29.04.02
Date de dépôt:

Anmelder/Applicant(s)/Demandeur(s):

Ciba Specialty Chemicals Holding Inc.
Klybeckstrasse 141
4057 Basel
SUISSE

Bezeichnung der Erfindung/Title of the invention/Titre de l'invention:
(Falls die Bezeichnung der Erfindung nicht angegeben ist, siehe Beschreibung.
If no title is shown please refer to the description.
Si aucun titre n'est indiqué se référer à la description.)

Compositions and methods for imparting improved rheology on pigment based inks
and paints

In Anspruch genommene Priorität(en) / Priority(ies) claimed /Priorité(s)
revendiquée(s)
Staat/Tag/Aktenzeichen/State/Date/File no./Pays/Date/Numéro de dépôt:

Internationale Patentklassifikation/International Patent Classification/
Classification internationale des brevets:

C09D11/00

Am Anmeldetag benannte Vertragstaaten/Contracting states designated at date of
filing/Etats contractants désignées lors du dépôt:

AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU MC NL PT SE TR

Compositions and methods for imparting improved rheology on pigment based inks and paints.

The present invention is directed to pigment compositions containing besides an organic pigment at least two coloured compounds of opposing charge, and ink/paint compositions containing same.

The ink/paint compositions show improved rheological (flow) performance and no loss or almost no loss in colour strength.

In order to improve the flow properties of pigment compositions, it is known from GB-A-1'356'253 to incorporate in diarylide pigments (1) water-soluble azo dyestuffs which have the same general chemical structure as the pigment but contain acidic groups and (2) fatty alcohols, fatty acids, fatty esters or fatty amines.

One of the pair of agents (1) and (2) is not coloured and therefore does not contribute colour intensity to the pigment composition. In addition the non-coloured portion can interfere with the performance of other pigment additives, e.g. lithographic properties of resulting inks can be affected leading to printing problems.

US-A-4'461'647 describes so-called fluidized agents which are water-insoluble asymmetric dyestuffs substituted by long chain ammonium salts which are added to pigment dispersions in order to enhance their fluidity and flocculation resistance.

Fluidizing agents are restricted to pigment derivatives and can suffer from colour strength loss, lithographic problems and interference with other pigment additives.

There is a need in pigment industry, therefore, to pigment compositions to be used in inks and paints with improved rheological properties (stability to flocculation) and good coloristic effects.

It has now been found surprisingly that pigment compositions comprising an organic pigment and a combination (complex) of at least two, normally water-soluble, coloured compounds (dyes) of opposing charge, e.g. of at least one anionic and one cationic dye, which dyes are readily available ones, as dispersants for the pigment, can largely overcome the mentioned problems of conventional pigment compositions.

It is assumed that the dyes of opposing charge are complexed in such a way as to be retained within the pigment composition. Alternatively, the retention of both the dyes by separate desolubilisation mechanisms is also possible.

Accordingly, the present invention provides in a first aspect, a pigment composition of (1) an organic pigment and (2) a combination of at least one anionic and at least one cationic coloured compound wherein the combination (2) comprises

(a) at least one anionic and at least one cationic dye, each of a chemical structure differing from that of the organic pigment (1),

(b) at least one anionic and at least one cationic pigment derivative, the chemical structure of at least one of which is not derived from said organic pigment (1); or

(c) mixtures of (a) and (b).

In a second aspect, the present invention provides said pigment composition as a solid composition, preferably as a pigment powder or as pigment granules.

In a further aspect, the present invention provides a non-aqueous composition, preferably a non-aqueous pigment dispersion.

In another aspect, the present invention provides methods for preparing said solid or non-aqueous pigment compositions.

In yet another aspect, the present invention provides non-aqueous inks or paints (oil ink or paint compositions, based e.g. on petroleum distillates) containing said pigment dispersions, and methods for preparing them.

In yet another aspect, the present invention provides the use of said non-aqueous inks or paints (ink or paint compositions) in printing and paint systems.

These and further aspects of the present invention will be described in the following.

The basis for the inventive pigment composition can be from the range of organic pigments such as, but not exclusively, monoazo, disazo, naphthol, dioxazone, azomethine, azocondensation, metal complex, nitro, perinone, quinoline, anthraquinone,

benzimidazolone, isoindoline, isoindolinone, quinacridone, hydroxyanthraquinone, aminoanthraquinone, anthrapyrimidine, indanthrone, flavanthrone, pyranthrone, anthantrone, isoviolanthrone, diketopyrrolopyrrole, carbazole, perylene, indigo or thioindigo pigments.

Mixtures of the pigments may be used.

Examples of these pigments and also further pigments can be found in the monograph: W. Herbst, K. Hunger "Industrielle Organische Pigmente," 2nd edition, 1995, VCH Verlagsgesellschaft.

Preferred pigments for the application of the present invention are mono- or disazo pigments, preferably mono- or diarylides, or metal complexes, preferably a copper phthalocyanine pigment, or naphthol pigments, preferably β -naphthol or a β -oxynaphthoic acid (BONA) pigments.

More preferably, the following organic pigments are used inventively:

Mono- or diarylide yellow pigments selected from C.I. Pigment Yellow 1, 2, 10, 12, 13, 14, 17, 61, 62, 63, 64, 65, 73, 74, 75, 83, 127, 168, 174, 176, 188 and 191.

Monoarylide yellow pigments selected from C.I. Pigment Yellow 1, C.I. Pigment Yellow 2, C.I. Pigment Yellow 65, C.I. Pigment Yellow 73, C.I. Pigment Yellow 74 and C.I. Yellow 75.

Diarylide yellow pigments selected from C.I. Pigment Yellow 12, C.I. Pigment Yellow 13, C.I. Pigment Yellow 14, C.I. Pigment Yellow 17 and C.I. Pigment Yellow 83.

Disazo orange pigments selected from C.I. Pigment Orange 16 and C.I. Pigment Orange 34.

Naphthol red pigments selected from C.I. Pigment Red 48:1, C.I. Pigment Red 48:2, C.I. Pigment Red 48:3, C.I. Pigment Red 48:4, C.I. Pigment Red 48:5, C.I. Pigment Red 49:1, C.I. Pigment Red 52:1, C.I. Pigment Red 52:2, C.I. Pigment Red 52:3, C.I. Pigment Red 53:1, C.I. Pigment Red 53:2, C.I. Pigment Red 53:3, C.I. Pigment Red 57:1, C.I. Pigment Red 57:2, C.I. Pigment Red 58:2, C.I. Pigment Red 58:4, C.I. Pigment Red 63:1 and C.I. Pigment Red 64:1.

Blue or green copper phthalocyanine pigments selected from C.I. Pigment Blue 15:3, C.I. Pigment Blue 15:4, C.I. Pigment Green 7 and C.I. Pigment Green 36.

The anionic dyes are typically, but not exclusively, commercially available dyes selected from acid dyes, direct dyes, reactive dyes and mordant dyes. As a rule, their chemical structure is different from that of the organic pigment.

Preferred are the following anionic dyes to be used inventively:

Acid dyes selected from C.I. Acid Black 1, 24 and 48, C.I. Acid Blue 1, 7, 9, 25, 29, 40, 45, 74, 80, 83, 90, 92, 113, 120, 129 and 147, C.I. Acid Green 1, 3, 5, 25, 27, and 50, C.I. Acid Orange 6, 7, 8, 10, 12, 51, 52, 63 and 74, C.I. Acid Red 1, 4, 8, 14, 17, 18, 26, 27, 29, 37, 44, 50, 51, 52, 66, 73, 88, 97, 103, 114, 150, 151 and 183, C.I. Acid Violet 7 and 17, and C.I. Acid Yellow 1, 9, 11, 17, 23, 25, 29, 34, 36, 42, 54, 76, 99 and 169.

Direct dyes selected from C.I. Direct Blue 1, 14, 53 and 71, C.I. Direct Violet 51, C.I. Direct Red 2, 23, 28, 75, 80 and 81, and C.I. Direct Yellow 4, 8, 9, 12, 27, 50, 62 and 172.

Reactive dyes selected from C.I. Reactive Black 5, C.I. Reactive Blue 2, 4 and 15, C.I. Reactive Orange 16, C.I. Reactive Red 2 and 4, and C.I. Reactive Yellow 2.

Mordant dyes selected from C.I. Mordant Black 17 and C.I. Mordant Violet 5.

One or more anionic dyes can be used in the inventive pigment compositions.

The anionic dyes may also be pigment derivatives bearing one or more acidic groups which impart to them a (certain) water solubility. The anionic pigment derivative may be a derivative of organic pigment (1), on the one hand, but also need not to be of similar structure to organic pigment (1), on the other hand.

As a rule, the anionic pigment derivatives give good results when associated with a non-derivative cationic dye.

Preferred anionic pigment derivatives are those derived from the preferred pigments mentioned hereinbefore.

The cationic dyes are typically, but not exclusively, also commercially available dyes which may be - according to their chemical characterization - azo, azomethine, methine, polymethine, azine, cyanine, oxazine, thiazine, thiazole, acridine, anthraquinone, triarylmethane, xanthene or ketone imine dyes. Their chemical structure is generally different from that of pigment (1).

Preferred are the following cationic dyes to be used inventively:

Cationic black dyes selected from C.I. Basic Black 2 and C.I. Basic Black 7.

Cationic blue dyes selected from C.I. Basic Blue 1, 3, 6, 7, 9, 11, 12, 16, 17, 24, 26, 40, 41, 57, 66, 80, 123 and 159.

Cationic green dyes selected from C.I. Basic Green 1, 4 and 5.

Cationic orange dyes selected from C.I. Basic Orange 2, 14, 21 and 54.

Cationic red dyes selected from C.I. Basic Red 1, 2, 5, 9, 10, 13, 22, 29, 46 and 54.

Cationic violet dyes selected from C.I. Basic Violet 1, 2, 3, 4, 10 and 35.

Cationic yellow dyes selected from C.I. Basic Yellow 1, 2, 11, 13, 17, 19, 21, 24, 28, 40, 45, 53, 61, 63 and 73.

One or more cationic dyes can be used in the inventive pigment compositions.

The cationic dye may also be a pigment derivative bearing one or more basic (basic means cationic) groups which impart to them a (certain) water solubility. The cationic pigment derivative may be a derivative of organic pigment (1), on the one hand, but also need not to be of similar structure to organic pigment (1), on the other hand.

Preferred cationic pigment derivatives are those derived from the preferred pigments mentioned hereinbefore.

The cationic pigment derivatives can be combined with non-derivative anionic dyes to give good results, too.

When a combination of an anionic and a cationic pigment derivative is used in the inventive pigment compositions, one of said pigment derivatives is not derived from organic pigment (1), i.e. this derivative has to show a different chemical structure from the base structure of organic pigment (1).

Combination (2) of the inventive pigment compositions preferably comprises such pairs as:
positively charged dye + negatively charged dye
positively charged pigment derivative + negatively charged dye
positively charged dye + negatively charged pigment derivative
positively charged pigment derivative + negatively charged pigment derivative
(the two derivatives must be structurally different)

Alternatively, it has been found that at least a partial replacement of the anionic/cationic coloured compound (anionic/cationic dye or anionic/cationic pigment derivative) with an anionic/cationic surfactant, respectively, can also lead to inventive pigment compositions with sufficient performance. Up to about 1/3 (0 to 0.33 mole%) of the anionic/cationic dye (anionic/cationic pigment derivative) can be replaced by an anionic/cationic surfactant, respectively.

Suitable surfactants are known to those skilled in the art. Preferably they comprise e.g. long chain (fatty) alcohols, acids, esters or amines and their derivatives, such as alkoxylates (ethoxylates), which contain positively/negatively charged groups.

In this context, reference is made to the relevant textbooks, scientific or technical publications.

Preferred pairs of combination (2) – when anionic/cationic surfactants are used – comprise:
positively charged dye/positively charged surfactant + negatively charged dye
positively charged pigment derivative/ positively charged surfactant + negatively charged dye
positively charged pigment derivative/ positively charged surfactant + negatively charged pigment derivative (the two derivatives must be structurally different)
negatively charged pigment derivative/ negatively charged surfactant + positively charged dye.

C.I. means Colour Index as compiled by the by The Society of Dyers and Colourists and The American Association of Textile Chemists and Colourists.

Details, such as descriptions and definitions, for the mentioned pigments, the anionic dyes as acid, direct, reactive and mordant dyes, and the cationic (basic) dyes can be found there.

The inventive compositions of organic pigments or organic pigment compositions (the latter may include typical additives such as abietyl resins, other rheology modifiers and ink vehicle components) may contain usually from 50.1 to 99.8% by weight (b.w.), preferably from 80.0 to 99.0% (b.w.) of the pigment, usually from 0.1 to 49.8% (b.w.), preferably from 0.5 to 10.0% (b.w.) of at least one anionic coloured compound (dye), and usually from 0.1 to 49.8% (b.w.), preferably from 0.5 to 10% (b.w.) of at least one cationic coloured compound (dye).

Aqueous preparations of these compositions have a solids content usually from about 0.5% to 20%, preferably from 5 to 18%. Organic pigment dispersions can be prepared from dry pigments, by use of additional surfactants, at a level of at least 50% pigment by conventional techniques.

In non-aqueous lithographic inks, pigment concentration normally is 8 to 20%. Ink concentrates, where rheology modifiers can be particularly useful, can contain up to 50% (0.5 to 50%) pigment. In certain circumstances, low pigment concentration below about 5% is also possible.

The (non-aqueous) pigment compositions may optionally contain further additives such as, but not exclusively, e.g. abietyl resins and abietyl derivatives, surfactants, pigment derivatives, extenders, ink vehicle components, rheology modifiers, etc.

Effective amounts should be used, e.g. from 0 to 50% (b.w.), based on the combined weight of the pigment and the dyes.

The dyes may be used as a solution or dispersion in water or other suitable solvent.

The dyes may also be used in press-cake, granule or dry powder form.

The dye mixture (complex of anionic and cationic dye(s)) may also deliberately be formed and isolated prior to use and utilised as a solution or dispersion in water or other suitable solvent.

The dye complex may also be used in press-cake, granule or dry powder form.

The anionic/cationic coloured compound (dye) may be incorporated independently or together into a pigment preparation, preferably a water-based composition (dispersion), during or after its preparation by standard stirring/milling techniques.

Alternatively the dyes or dye complexes may be incorporated into the pigment during its synthesis, i.e. before or after coupling, but more preferably after completion of coupling, but before isolation, washing or drying.

When preparing inventive pigment compositions in solid form, such as pigment powders or pigment granules, the method comprises e.g. heating an aqueous pigment slurry (as obtained by normal synthesis steps) containing the necessary additives, to induce flocculation, followed by cooling and isolation which comprises such steps as filtering and washing until salt free, and then drying and/or granulating the composition.

Alternatively, the method can be started by a dispersion step for the pigment in an aqueous solution of the dyestuffs (at least one anionic and at least one cationic dye).

The inventive pigment compositions may be used in all customary industrial printing processes such as lithographic, flexographic, gravure, letterpress, screen, ink-jet, intaglio, aqueous or other printing inks, further in all customary industrial paint systems such as decorative, industrial, automotive or other paint systems, to provide improved rheology with no or at most minimalized reduction of colour strength.

The method of preparation of the ink system is by methods of shear to induce dispersion into a varnish system. Examples of the wide range of techniques are triple-roll-mill and bead mill. Varnish systems are also wide ranging and known by the artisan.

Examples of the final application are off-set lithography and sheet fed.

Alternatively, when preparing the printing inks or paint systems, the dyes may be incorporated independently or together (dye complexes) to a conventional ink or paint formulation before, during or after pigment addition.

For the preparation of the inks and paints corresponding high molecular weight organic substances, such as binders, synthetic resin dispersions etc. and the inventive pigment compositions are usually dispersed or dissolved together, optionally together with customary additives, such as dispersants, fillers, paint auxiliaries, siccatives, plasticizers and/or additional pigments or pigment precursors, in a common solvent or mixture of solvents. This can be achieved by dispersing or dissolving the individual components by themselves, or

also several components together, and only then bringing all components together, or by adding everything together simultaneously.

It is the use of at least two dyes of opposing charge (dye complex) as part of a pigment composition which gives the inventive pigment compositions their particularly useful properties and advantageous effects, i.e. their improved rheological (flow) performance combined with no or at most a minimum loss in colour strength, over pigment compositions of the state of the art.

The desired effects and the other by-properties can be moderated by the appropriate selection of the relative ratio and total amount of the two dyes. The dyes should also be selected that undesirable effects on product shade do not occur. As the pair of materials (dye complex) which are responsible for the improved rheological performance are both coloured, in general of the the same colour, almost no loss in colour strength is observed.

The present invention is further illustrated by, but not restricted to, the following examples in which all parts and percentages are by weight unless otherwise indicated. The temperatures are given in degrees centigrade.

Examples:

Example 1

To a stirred C.I. Pigment Yellow 13 aqueous slurry containing 63 g of the pigment, an aqueous solution containing 2 g of 4,4'-bis[[1-[[[(2,4-dimethylphenyl)amino]carbonyl]-2-oxopropyl]azo]-[1,1'-biphenyl]-2,2'-disulphonic acid is added, followed by an aqueous solution containing 3.5 g of C.I. Basic Yellow 40. Following this an aqueous solution of Burez K50-505A potassium salt (potassium soap of disproportionated rosin, 50%, Eka-Nobel), containing the equivalent of 30 g resin acids, is added and the resulting slurry heated to roughly 95°C by direct steam injection.

The slurry is acidified by dropwise addition of dilute hydrochloric acid, then cooled, filtered and washed until salt free. The product presscake is dried giving 94 g (= 95% yield).

The resulting dye pair is thus formed in situ during pigment processing.

Example 2

The Example 1 procedure is repeated with 64 g of C.I. Pigment Yellow 13 plus 2.5 g of C.I. Basic Yellow 28 in place of C.I. Basic Yellow 40.

Example 3

The Example 1 procedure is repeated with 63.8 g of C.I. Pigment Yellow 13 plus 1.7 g of C.I. Basic Yellow 17 in place of C.I. Basic Yellow 40.

Example 4

The Example 1 procedure is repeated with 64.1 g of C.I. Pigment Yellow 13 plus 2.4 g of C.I. Basic Yellow 13 in place of C.I. Basic Yellow 40.

Example 5

The Example 1 procedure is repeated with 64 g of C.I. Pigment Yellow 13 plus 2.5 g of C.I. Basic Yellow 45 in place of C.I. Basic Yellow 40.

Comparative Examples A to D:

Example A

The Example 1 procedure is repeated with 66.5 g of C.I. Pigment Yellow 13 and no added C.I. Basic Yellow 40.

Example B

The Example 1 procedure is repeated with 68.5 g of C.I. Pigment Yellow 13 and no additions of either C.I. Basic Yellow 40 or 4,4'-bis[[1-[(2,4-dimethylphenyl)amino]carbonyl]-2-oxypropyl]azo]-[1,1'-biphenyl]-2,2'-disulphonic acid.

Example C

The Example 1 procedure is repeated with 65 g of C.I. Pigment 13 but in absence of 4,4'-bis[[1-[(2,4-dimethylphenyl)amino]carbonyl]-2-oxypropyl]azo]-[1,1'-biphenyl]-2,2'-disulphonic acid.

Example D

The Example 1 procedure is repeated with 66 g of C.I. Pigment 13 but in absence of 4.4'-bis[[1-[[[(2,4-dimethylphenyl)amino]carbonyl]-2-oxypropyl]azo]-[1,1'-biphenyl]-2,2'-disulphonic acid. 2.5 g of C.I. Basic Yellow is also used in place of C.I. Basic Yellow 45.

Example 6

A stirred aqueous slurry containing C.I. Pigment Blue 15:3 (β -copper phthalocyanine) is heated to 90°C. A slurry containing 2.5 g of copper phthalocyanine monosulfonic acid is added and stirring continued for 30 minutes. An aqueous solution containing the equivalent of 4 g of C.I. Basic Blue 9 (Methylene Blue) is then added and stirring continued for 30 minutes more. The resulting slurry is cooled, filtered and washed until salt free, then dried giving 58 g of pigment composition.

Example 7

To a stirred aqueous slurry of 6.1 g of copper phthalocyanine monosulfonic acid at pH of 11 is added 3.49 g of C.I. Basic Blue 9. An aqueous solution containing 3.25 g of dodecylbenzene-p-sulfonic acid, sodium salt, is added and then the resulting slurry is filtered and dried, giving a yield of 9.58 g (78%).

This dry complex is added at a 3% level to a stirred aqueous slurry of C.I. Pigment Blue 15:3 at 30°C and pH 1. After stirring for 1 hour the slurry is filtered, washed until salt free and dried.

Example 8

To a stirred aqueous slurry of 12.12 g of copper phthalocyanine monosulfonic acid at pH of 11 is added 3.74 g of C.I. Basic Blue 9 and the the resulting slurry is filtered and dried giving a yield of 11.84 g (74%).

This dry complex is added at a 3% level to a stirred aqueous slurry of C.I. Pigment Blue 15:3 at 30°C and pH 1. After stirring for 1 hour the slurry is filtered, washed until salt free and dried.

Comparative Examples E to G:

Example E

The Example 6 procedure is repeated in the absence of C.I. Basic Blue 9.

Example F

The Example 6 procedure is repeated in the absence of both C.I. Basic Blue 9 and copper phthalocyanine monosulfonic acid.

Example G

The Example 8 procedure is repeated in the absence of both C.I. Basic Blue 9 and copper phthalocyanine monosulfonic acid.

Test Method:

The products of the foregoing examples were used to prepare aqueous dispersions containing 20% pigmentation which are tested into a commercial heatset varnish system on a Buhler SDY-200 three roll mill.

The inks are then reduced to between 12 to 16% pigmentation (depending on the pigment type) by the addition of further varnish.

Colouristic assessment is carried out on the prints produced from a Prufbau Printer and low shear flow assessed on a 45° angled plate after 2 or 24 hours, depending on the the pigment type (2 hours for yellow pigment compositions, 24 hours for blue pigment compositions).

The figures in Table 1 are quoted in comparison to a commercial pigment standard (low shear flow and colour strength – 100%, each).

Table 1:

Example No,	Low Shear Flow [%]	Colour Strength [%]
1	195	100
2	150	110
3	140	100
4	130	100
5	140	100
A (Comparison)	95	105
B (Comparison)	90	110
C (Comparison)	90	110
D (Comparison)	110	95
6	290	100
7	220	100
8	160	100
E (Comparison)	170	100
F (Comparison)	100	100
G (Comparison)	100	100

Example 9

This example relates to an isolated complex of a dyestuff pair as an ink additive.

An 80ml aqueous solution containing 2.0g 4,4'-bis[[1-[(2,4-dimethylphenyl)amino]carbonyl]-2-oxypropyl]azo]-[1,1'-biphenyl]-2,2'-disulphonic acid is mixed thoroughly with an 80ml aqueous solution containing the equivalent of 1.5g cation weight of Basic Yellow 28. To this mixture a 45ml aqueous solution of Burez K50-505A potassium salt, containing the equivalent of 1.6g resin acids, is added resulting in increased alkalinity (pH 9.5). The mixture is heated to 60°C and the pH reduced to 5.0 by the addition of dilute hydrochloric acid. The resulting material was filtered, washed and dried giving a 90% yield. The dry product is ground and blended with a standard diarylide yellow composition (Pigment Yellow 174) at a weight ratio of 1:19 respectively.

Table 2:

	Low shear flow	Strength
Example 9	240%	102%
Comparative Example H (Pigment Yellow 174 alone)	100%	100%

Claims:

1. A pigment composition of (1) an organic pigment and (2) a combination of at least one anionic and at least one cationic coloured compound wherein the combination (2) comprises
(a) at least one anionic and at least one cationic dye, each of a chemical structure differing from that of the organic pigment (1),
(b) at least one anionic and at least one cationic pigment derivative, the chemical structure of at least one of which is not derived from said organic pigment (1), or
(c) mixtures of (a) and (b).
2. The pigment composition according to claim 1 wherein the organic pigment is a monoazo, disazo, naphthol, dioxazone, azomethine, azocondensation, metal complex, nitro, perinone, quinoline, anthraquinone, benzimidazolone, isoindoline, isoindolinone, quinacridone, hydroxyanthraquinone, aminoanthraquinone, anthrapyrimidine, indanthrone, flavanthrone, pyranthrone, anthanthrone, isoviolanthrone, diketopyrrolopyrrole, carbazole, perylene, indigo or thioindigo pigment.
3. The pigment composition according to claim 2 wherein the organic pigment is a mono- or disazo pigment, preferably a mono- or diarylide, or a metal complex, preferably a copper phthalocyanine pigment.
4. A pigment composition according to claim 2 wherein the organic pigment is a naphthol pigment, preferably a β -naphthol or a β -oxynaphthoic acid (BONA) pigment.
5. The pigment composition according to claim 3 wherein the organic pigment is a mono- or diarylide yellow pigment selected from C.I. Pigment Yellow 1, 2, 10, 12, 13, 14, 17, 61, 62, 63, 64, 65, 73, 74, 75, 83, 127, 168, 174, 176, 188 and 191.
6. The pigment composition according to claim 5 wherein the organic pigment is a monoarylide yellow pigment selected from C.I. Pigment Yellow 1, C.I. Pigment Yellow 2, C.I. Pigment Yellow 65, C.I. Pigment Yellow 73, C.I. Pigment Yellow 74 and C.I. Yellow 75.
7. The pigment composition according to claim 5 wherein the organic pigment is a diarylide yellow pigment selected from C.I. Pigment Yellow 12, C.I. Pigment Yellow 13, C.I. Pigment Yellow 14, C.I. Pigment Yellow 17 and C.I. Pigment Yellow 83.

8. The pigment composition according to claim 3 wherein the organic pigment is a disazo orange pigment selected from C.I. Pigment Orange 16 and C.I. Pigment Orange 34.

9. The pigment composition according to claim 4 wherein the organic pigment is a naphthol red pigment selected from C.I. Pigment Red 48:1, C.I. Pigment Red 48:2, C.I. Pigment Red 48:3, C.I. Pigment Red 48:4, C.I. Pigment Red 48:5, C.I. Pigment Red 49:1, C.I. Pigment Red 52:1, C.I. Pigment Red 52:2, C.I. Pigment Red 52:3, C.I. Pigment Red 53:1, C.I. Pigment Red 53:2, C.I. Pigment Red 53:3, C.I. Pigment Red 57:1, C.I. Pigment Red 57:2, C.I. Pigment Red 58:2, C.I. Pigment Red 58:4, C.I. Pigment Red 63:1 and C.I. Pigment Red 64:1.

10. The pigment composition according to claim 3 wherein the organic pigment is a blue or green copper phthalocyanine pigment selected from C.I. Pigment Blue 15:3, C.I. Pigment Blue 15:4, C.I. Pigment Green 7 and C.I. Pigment Green 36.

11. The pigment composition according to claim 1 wherein the anionic dye is selected from acid dyes, direct dyes, reactive dyes and mordant dyes.

12. The pigment composition according to claim 1 wherein the anionic dye is an organic pigment derivative containing one or more acidic groups.

13. The pigment composition according to claim 11 wherein the anionic dye is an acid dye selected from C.I. Acid Black 1, 24 and 48, C.I. Acid Blue 1, 7, 9, 25, 29, 40, 45, 74, 80, 83, 90, 92, 113, 120, 129 and 147, C.I. Acid Green 1, 3, 5, 25, 27, and 50, C.I. Acid Orange 6, 7, 8, 10, 12, 51, 52, 63 and 74, C.I. Acid Red 1, 4, 8, 14, 17, 18, 26, 27, 29, 37, 44, 50, 51, 52, 66, 73, 88, 97, 103, 114, 150, 151 and 183, C.I. Acid Violet 7 and 17, and C.I. Acid Yellow 1, 9, 11, 17, 23, 25, 29, 34, 36, 42, 54, 76, 99 and 169.

14. The pigment composition according to claim 11 wherein the anionic dye is a direct dye selected from C.I. Direct Blue 1, 14, 53 and 71, C.I. Direct Violet 51, C.I. Direct Red 2, 23, 28, 75, 80 and 81, and C.I. Direct Yellow 4, 8, 9, 12, 27, 50, 62 and 172.

15. The pigment composition according to claim 11 wherein the anionic dye is a reactive dye selected from C.I. Reactive Black 5, C.I. Reactive Blue 2, 4 and 15, C.I. Reactive Orange 16, C.I. Reactive Red 2 and 4, and C.I. Reactive Yellow 2.

16. The pigment composition according to claim 11 wherein the anionic dye is a mordant dye selected from C.I. Mordant Black 17 and C.I. Mordant Violet 5.

17. The pigment composition according to claim 1 wherein the cationic dye is a(n) azo, azomethine, methine, polymethine, azine, cyanine, oxazine, thiazine, thiazole, acridine, anthraquinone, triarylmethane, xanthene or ketone imine dye.

18. The pigment composition according to claim 1 wherein the cationic dye is an organic pigment derivative containing one or more basic groups.

19. The pigment composition according to claim 17 wherein the cationic dye is a black dye selected from C.I. Basic Black 2 and C.I. Basic Black 7.

20. The pigment composition according to claim 17 wherein the cationic dye is a blue dye selected from C.I. Basic Blue 1, 3, 6, 7, 9, 11, 12, 16, 17, 24, 26, 40, 41, 57, 66, 80, 123 and 159.

21. The pigment composition according to claim 17 wherein the cationic dye is a green dye selected from C.I. Basic Green 1, 4 and 5.

22. The pigment composition according to claim 17 wherein the cationic dye is an orange dye selected from C.I. Basic Orange 2, 14, 21 and 54.

23. The pigment composition according to claim 17 wherein the cationic dye is a red dye selected from C.I. Basic Red 1, 2, 5, 9, 10, 13, 22, 29, 46 and 54.

24. The pigment composition according to claim 17 wherein the cationic dye is a violet dye selected from C.I. Basic Violet 1, 2, 3, 4, 10 and 35.

25. The pigment composition according to claim 17 wherein the cationic dye is a yellow dye selected from C.I. Basic Yellow 1, 2, 11, 13, 17, 19, 21, 24, 28, 40, 45, 53, 61, 63 and 73.

26. The pigment composition according to claim 1 wherein combination (2) comprises an anionic pigment derivative and a cationic pigment derivative, one of said derivatives being not derived from organic pigment (1).

27. The pigment composition according to claim 1 wherein combination (2) comprises the pairs of

cationic (positively charged) dye + anionic (negatively charged) dye,

cationic (positively charged) pigment derivative + anionic (negatively charged) dye, or

cationic (positively charged) dye + anionic (negatively charged) pigment derivative.

28. The pigment composition according to claim 1 containing from 50.1 to 99.8% by weight (b.w.), preferably from 80.0 to 99.0% (b.w.) of the organic pigment (1), from 0.1 to 49.8% (b.w.), preferably from 0.5 to 10.0% (b.w.) of at least one anionic coloured compound, and from 0.1 to 49.8% (b.w.), preferably from 0.5 to 10% (b.w.) of at least one cationic coloured compound.

29. The pigment composition according to claim 28 containing further additives.

30. The pigment composition according to claim 1 which is an aqueous composition, preferably a pigment dispersion, of organic pigment (1) and said anionic and cationic coloured compounds.

31. The pigment composition according to claim 1 which is a solid composition, preferably a pigment powder or pigment granules.

32. Method for preparing the pigment composition according to claim 30 comprising adding said anionic and cationic coloured compounds to the organic pigment (1) during its synthesis, or adding a separately prepared and isolated complex of said anionic and cationic coloured compounds to the organic pigment (1).

33. Method for preparing the pigment composition according to claim 31 comprising dispersing the organic pigment in aqueous solutions of said anionic and cationic coloured compounds, cooling the dispersion, filtering and washing until salt free, and then drying and/or granulating the obtained presscake.

34. A non-aqueous printing ink composition or paint system comprising the pigment composition according to claim 1.

35. A method for preparing a non-aqueous printing ink composition or paint system according to claim 32 comprising adding said pigment compositions to a conventional printing ink formulation or paint system.

36. Use of the non-aqueous printing ink compositions or paint systems according to claim 32 in printing and painting procedures.

Abstract:

Pigment compositions comprising an organic pigment and a combination of at least two normally water-soluble colored compounds (dyes) of opposing charge, i.e. of at least one anionic and one cationic dye are provided. The compositions impart improved rheology on non-aqueous pigment based printing inks and paints.

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☒ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.